

ABSTRACT OF THE DISCLOSURE

A method of producing a positive electrode active material for a non-aqueous electrolyte secondary battery, comprising the steps of: (a) preparing a raw material mixture, comprising "nx" mol of magnesium, "ny" mol of an element M where the element M is at least one selected from the group consisting of Al, Ti, Sr, Mn, Ni and Ca, "n(1-x-y)" mol of cobalt and "nz" mol of lithium, such that the values n, x, y and z satisfy $0 < n$, $0.97 \leq (1/z) \leq 1$, $0.005 \leq x \leq 0.1$, and $0.001 \leq y \leq 0.03$; and (b) baking the raw material mixture in an oxidization atmosphere at 1000 to 1100 °C.